



AOS NON-SILICONE XT-2

Product Code: 52030



TECHNICAL DATA SHEET

Product Description

AOS Non-Silicone XT-2 Heat Sink Compound is recommended for *high-temperature heat transfer* in silicone sensitive applications. **Non-Silicone XT-2** is a non-silicone-based thermally conductive white paste/grease, compounded with 100% synthetic base stocks. The product offers high thermal conductivity and virtually no bleed or evaporation over a wide operating temperature range.

Product Benefits and Features

Stable at continuous operating temperatures **up to 250°C** with the same unique advantages of our standard non-silicone heat sink compound. Nonflammable, oxidation resistant, and does not promote rust or corrosion. No bleed; excellent thermal resistance and high thermal conductivity; efficient thermal coupler; effective and positive heat sink sealers and heat transfer agent. 5-year minimum shelf life. Compatible with rubber and plastic.

Major Applications

While suitable for traditional applications requiring a non-silicone thermal grease, **Non-Silicone XT-2** is especially appropriate when there is an intentional heat source, such as a heating element, calrod, etc., that requires continuous operation at temperatures exceeding 200°C.

Methods of Application

By hand brushing or wiping. Also, automatic dispensing methods save labor and material.

Typical Properties

<u>Property</u>	<u>Value</u>	<u>Test Method</u>
Consistency (Penetration, worked, 60x)	250 - 350	ASTM D-217
Specific Gravity , @ 25°C	2.4	ASTM D-70
Bleed , @ 200°C, 24 Hrs., %/Wt	0.20	FTM-321 MODIFIED
Evaporation , @ 200°C, 24 Hrs., %/Wt.	0.50	FTM-321 MODIFIED
Thermal Conductivity , @ 36°C W/m-K	0.95	ASTM D 5470-06
Thermal Resistance @ 50°C °C/W	0.3207	Oracle TTV 270-7806-01
Electrical Properties		
Dielectric strength, 0.05" gap, V/mil	353	ASTM D-149
Dielectric constant, 25°C @ 1,000 Hz	4.86	ASTM D-150
Dissipation factor, 25°C @ 1,000 Hz	0.0019	ASTM D-150
Volume Resistivity, ohm-cm	7.28 x 10 ¹³	ASTM D-257
Operating Temperature Range	-40°C to 250°C	
Flow Rate grams/min.	2 to 5	AOS Method
Appearance	White Paste	

Please know that customers are responsible for testing AOS Thermal Compounds materials for their proposed use. Any information furnished by AOS Thermal Compounds and its agents is believed to be reliable, but AOS Thermal Compounds does not guarantee the results to be accurate and makes no warranties as to the fitness, merchantability, or suitability of any AOS material or product for any specific or general use and shall not be held liable for incidental or consequential damages of any kind. (040201)

22 Meridian Road, Suite 6, Eatontown, New Jersey 07724

732-389-5514 • fax 732-389-6380 • e-mail sales@aosco.com • web <http://www.aosco.com>