



AOS 340 LR

Product Code: 52054



TECHNICAL DATA SHEET

Product Description

AOS 340 LR (lowest resistance) is a non-silicone thermal grease with the current lowest thermal resistance on the market (for thin bond line applications*). AOS 340 LR is also extremely durable and will not pump-out making it ideal for applications requiring extended life and no degradation.

* For larger gaps/thicker films use a high thermal conductivity material such as 52050, 52060 or Sure-form gap filler.

Product Features & Benefits

AOS 340 LR is non-silicone based, non-reactive, and non-abrasive with a soft, grease-like consistency with thixotropic behavior. It has excellent dielectric properties, lowest thermal resistance and superior durability (will not pump-out).

Major Applications

AOS 340 LR is designed to be applied where thermal coupling is required and where a device may need to be removed from the heat sink at a later time. Major applications include CPU/GPU, power semiconductors and LED's. It is also the most efficient and cost effective low bond line TIM 2 for use in any thermal management application

Typical Properties

<u>Property</u>	<u>Value</u>	<u>Test Method</u>
Consistency (Penetration, worked, 60x)	330-350	ASTM D-217
Specific Gravity , @ 25°C	3.0	ASTM D-70
Bleed , @ 150°C, 24 Hrs., %/Wt	0.0	FTM-321 MODIFIED
Evaporation , @ 150°C, 24 Hrs., %/Wt.	1.0	FTM-321 MODIFIED
Thermal Conductivity , @ 36°C W/m-K	1.3	ASTM D-5470-06
Thermal Resistance @ 50°C °C/W	0.0310	Oracle TTV 270-7806-01
Anticipated Minimum Bond line (mils) Based on filler dimensions	0.3 mils	
Electrical Properties		
Dielectric strength, 0.05" gap, V/mil	265	ASTM D-149
Dielectric constant, 25°C @ 1,000 Hz	5.02	ASTM D-150
Dissipation factor, 25°C @ 1,000 Hz	0.0022	ASTM D-150
Volume Resistivity, ohm-cm	2.0 X 10 ¹⁵	ASTM D-257
Operating Temperature Range	-40°C to 180°C	
Flow Rate grams/min.	5-10	AOS Method # 1
Appearance	Smooth White Paste	

22 Meridian Road, Suite 6, Eatontown, New Jersey 07724

732-389-5514 • fax 732-389-6380 • e-mail sales@aosco.com • web <http://www.aosco.com>