

ELECTRICALLY CONDUCTIVE GREASE

Product Code: 57000

TECHNICAL DATA SHEET



Product Description

AOS CONDUCTIVE GREASE is a NON-SILICONE-based, chemically inert heat sink compound that is thermally stable and nonflammable. This advanced grease offers *premium electrical and thermal conductivity*.

Major Applications

Thermal applications for compound include the dissipation of heat from high power electronic components such as power resistors, rectifiers, transistors and transformers.

Low power electronic applications include static drain, grounding, *soft* electronic connections, heat dissipation, and assembly protection. Compound can be used in high power electrical applications to improve the operational efficiency of high power switches and other sliding metal contacts.

| Property | Value | Test Method |
|---|----------------|------------------|
| Consistency (Penetration, worked, 60x) | 250-350 | ASTM D-217 |
| Specific Gravity, @ 25°C | N/A | ASTM D-70 |
| Bleed, @ 200°C, 24 Hrs., %/Wt | 0.50 | FTM-321 MODIFIED |
| Evaporation, @ 200°C, 24 Hrs., %/Wt. | 1.00 | FTM-321 MODIFIED |
| Thermal Conductivity, @ 36°C | | |
| W/m-K | 2.7 | ASTM D-5470-06 |
| Electrical Properties | | |
| Dielectric Strength, 0.5" gap, V/mil | N/A | ASTM D-149 |
| Dielectric Constant, 25°C @ 1,000 Hz | N/A | ASTM D-150 |
| Dissipation Factor, 25°C @ 1,000 Hz | N/A | ASTM D-150 |
| Volume Resistivity, ohm-cm | < 0.01 | ASTM D-257 |
| Operating Temperature Range | -40°C to 200°C | |
| Appearance | Smooth Paste | |

Typical Properties

Customers are responsible for testing AOS Thermal Compounds materials for their proposed use. Any information furnished by AOS Thermal Compounds and its agents is believed to be reliable, but AOS Thermal Compounds does not guarantee the results to be accurate and makes no warranties as to the fitness, merchantability, or suitability of any AOS material or product for any specific or general use and shall not be held liable for incidental or consequential damages of any kind. (040206)

22 Meridian Road, Suite 6, Eatontown, New Jersey 07724 (732) 389-5514 • fax (732) 389-6380 • e-mail <u>sales@aosco.com</u> • web http://www.aosco.com